

ALUMINUM COMMON GRADE 6061 WITH T4

Physical Properties	Metric	English
Density	2.70 g/cc	0.0975 lb/in ³
Mechanical Properties	Metric	English
Hardness, Brinell	65	65
Hardness, Knoop	88	88
Hardness, Vickers	75	75
Ultimate Tensile Strength	241	35
Tensile Yield Strength	145	21
Elongation at Break	22.00%	22.00%
Modulus of Elasticity	68.9 GPa	10000 ksi
Poissons Ratio	0.33	0.33
Fatigue Strength	96.5 MPa	14000 psi
Machinability	50.00%	50.00%
Shear Modulus	26.0 GPa	3770 ksi
Shear Strength	165 MPa	24000 psi
Electrical Properties	Metric	English
Electrical Resistivity	0.00000432 ohm-cm	0.00000432 ohm-cm
Thermal Properties	Metric	English
CTE, linear 68 ^o F	23.6 $\mu\text{m}/\text{m}\cdot\text{C}$	13.1 $\mu\text{in}/\text{in}\cdot\text{F}$
CTE, linear 250 ^o C	25.2 $\mu\text{m}/\text{m}\cdot\text{C}$	14.0 $\mu\text{in}/\text{in}\cdot\text{F}$
Specific Heat Capacity	0.896 J/g $\cdot\text{C}$	0.214 BTU/lb $\cdot\text{F}$
Thermal Conductivity	154 W/m-K	1070 BTU-in/hr-ft ² $\cdot\text{F}$
Melting Point	582 - 651.7 C	1080 - 1205 F
Solidus	582 C	1080 F
Liquidus	651.7 C	1205 F
Processing Properties	Metric	English
Solution Temperature	529 C	985 F
Aging Temperature	160 C	320 F
Material Components	Metric	English
Aluminum, Al	95.8 - 98.6 %	95.8 - 98.6 %
Chromium, Cr	0.0400 - 0.350 %	0.0400 - 0.350 %
Copper, Cu	0.150 - 0.400 %	0.150 - 0.400 %
Iron, Fe	\leq 0.700 %	\leq 0.700 %
Magnesium, Mg	0.800 - 1.20 %	0.800 - 1.20 %
Manganese, Mn	\leq 0.150 %	\leq 0.150 %
Other, each	\leq 0.0500 %	\leq 0.0500 %
Other, total	\leq 0.150 %	\leq 0.150 %
Silicon, Si	0.400 - 0.800 %	0.400 - 0.800 %
Titanium, Ti	\leq 0.150 %	\leq 0.150 %
Zinc, Zn	\leq 0.250 %	\leq 0.250 %

Alliance LLC 6061-T4

Alliance LLC
 1150 Eastport Center Dr.
 Valparaiso, IN. 46383

Tel: 219-548-3799
 Fax: 219-548-7071
 Email: sales@allianceorg.com