


www.Allianceorg.com



		Max	Min
Residual Induction Br	G	4,150	3,750
Coercive Force Hc	Oe	2,520	2,280
Intrinsic Coercive Force Hci	Oe	2,580	2,330
Max. Energy Product (BH)max	MGOe	3.6	3.2
Material Density	Lb/in ³		.177
Max. Operating Temperature	C		450
Temperature Coefficient for B	-%/C		.18
Temperature Coefficient for H	+%/C		.35
Required Magnetizing Force	Oe	20000	
Material Composition	Sr, Fe ₂ O ₃ , Si, Al		

Ferrite C-5

Ferrite magnets, also known as Ceramics, are the most widely used magnetic materials. Made of Iron Oxide, they are the least expensive magnets today. C-5 magnets are typically used in loudspeaker applications.

For more information please call or email Alliance technical support at:

Phone: 219-548-3799 Fax: 219-548-7071 email: engineering@allianceorg.com