

# PVC BACK-LIT

## Part Number: Laminated P 001-G

Item	Metric	Test Method
Weight	480±10 gsm	DIN53352 BS3424
Breaking Strength	635/451 N/5cm	DIN53354 BS3424
Tearing Strength	125/107 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (0305 18*12 G)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

## Part Number: Laminated P 002-G

Item	Metric	Test Method
Weight	610±10 gsm	DIN53352 BS3424
Breaking Strength	635/451 N/5cm	DIN53354 BS3424
Tearing Strength	125/107 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (0305 18*12 G)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

## Part Number: Laminated P 003-G

Item	Metric	Test Method
Weight	630±10 gsm	DIN53352 BS3424
Breaking Strength	950/875 N/5cm	DIN53354 BS3424
Tearing Strength	135/122 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (0505 18*12 G)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

## Part Number: Laminated P 004

Item	Metric	Test Method
Weight	650±10 gsm	DIN53352 BS3424
Breaking Strength	1100/1400 N/5cm	DIN53354 BS3424
Tearing Strength	130/180 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	

Lacquering	Products can be laquered with acrylic
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3
Ink Type	Solvent, Eco Solvent, UV, Screen Printing

**Part Number: Coated P 005-1-G**

Item	Metric	Test Method
Weight	440±10 gsm	DIN53352 BS3424
Breaking Strength	1300/1030 N/5cm	DIN53354 BS3424
Tearing Strength	115/105 N	DIN53356 BS3424
Adhesion	80 N/5cm	DIN53357 BS3424
Width	Up to 510cm (2525 36*36 G)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

**Part Number: Coated P 005-G**

Item	Metric	Test Method
Weight	510±10 gsm	DIN53352 BS3424
Breaking Strength	2100/1850 N/5cm	DIN53354 BS3424
Tearing Strength	300/250 N	DIN53356 BS3424
Adhesion	80 N/5cm	DIN53357 BS3424
Width	Up to 510cm (1010 20*20 G)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

**Part Number: Coated P 005-2-M**

Item	Metric	Test Method
Weight	610±10 gsm	DIN53352 BS3424
Breaking Strength	2100/1850 N/5cm	DIN53354 BS3424
Tearing Strength	300/250 N	DIN53356 BS3424
Adhesion	80 N/5cm	DIN53357 BS3424
Width	Up to 510cm (1010 20*20 M)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	