

# PVC BLOCK-OUT

## Part Number: Laminated P 009-W/G

Item	Metric	Test Method
Weight	440±10 gsm	DIN53352 BS3424
Breaking Strength	635/451 N/5cm	DIN53354 BS3424
Tearing Strength	125/107 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (0305 18*12)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

## Part Number: Laminated P 009-W/B

Item	Metric	Test Method
Weight	440±10 gsm	DIN53352 BS3424
Breaking Strength	635/451 N/5cm	DIN53354 BS3424
Tearing Strength	125/107 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (0305 18*12)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

## Part Number: Laminated P 010-W/G

Item	Metric	Test Method
Weight	440±10 gsm	DIN53352 BS3424
Breaking Strength	850/750 N/5cm	DIN53354 BS3424
Tearing Strength	185/135 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (0505 9*9)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

## Part Number: Laminated P 010-W/B

Item	Metric	Test Method
Weight	440±10 gsm	DIN53352 BS3424
Breaking Strength	850/750 N/5cm	DIN53354 BS3424
Tearing Strength	185/135 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (0505 9*9)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

Part Number: Coated P 016		
Item	Metric	Test Method
Weight	440±10      gsm	DIN53352 BS3424
Breaking Strength	1300/1030      N/5cm	DIN53354 BS3424
Tearing Strength	115/105      N	DIN53356 BS3424
Adhesion	80      N/5cm	DIN53357 BS3424
Width	Up to 350cm	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

Part Number: Coated P 017		
Item	Metric	Test Method
Weight	610±10      gsm	DIN53352 BS3424
Breaking Strength	1850/1350      N/5cm	DIN53354 BS3424
Tearing Strength	235/220      N	DIN53356 BS3424
Adhesion	80      N/5cm	DIN53357 BS3424
Width	Up to 350cm	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

Part Number: Coated Tarpaulin P 022		
Item	Metric	Test Method
Weight	800±20      gsm	DIN53352 BS3424
Breaking Strength	2250/2600      N/5cm	DIN53354 BS3424
Tearing Strength	370/320      N	DIN53356 BS3424
Adhesion	100      N/5cm	DIN53357 BS3424
Width	Up to 510cm      (1013)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic or PVDF	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	

Part Number: Coated Tarpaulin P 023		
Item	Metric	Test Method
Weight	900±20      gsm	DIN53352 BS3424
Breaking Strength	2250/2600      N/5cm	DIN53354 BS3424
Tearing Strength	370/320      N	DIN53356 BS3424
Adhesion	100      N/5cm	DIN53357 BS3424
Width	Up to 510cm      (1013)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic or PVDF	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	