

# PVC FRONT-LIT

## Part Number: Laminated P 006-1-G

Item	Metric	Test Method
Weight	280±10 gsm	DIN53352 BS3424
Breaking Strength	497/301 N/5cm	DIN53354 BS3424
Tearing Strength	85/65 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (0203 18*12 G)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

## Part Number: Laminated P 006-G

Item	Metric	Test Method
Weight	300±10 gsm	DIN53352 BS3424
Breaking Strength	497/301 N/5cm	DIN53354 BS3424
Tearing Strength	85/65 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (0203 18*12 G)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

## Part Number: Laminated P 007-1-G

Item	Metric	Test Method
Weight	320±10 gsm	DIN53352 BS3424
Breaking Strength	497/301 N/5cm	DIN53354 BS3424
Tearing Strength	85/65 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (0203 18*12 G)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

## Part Number: Laminated P 007-G


Item	Metric	Test Method
Weight	340±10 gsm	DIN53352 BS3424
Breaking Strength	497/301 N/5cm	DIN53354 BS3424
Tearing Strength	85/65 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (0203 18*12 G)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	

Lacquering	Products can be laquered with acrylic
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3
Ink Type	Solvent, Eco Solvent, UV, Screen Printing



**Part Number: Laminated P 008**

Item	Metric		Test Method
Weight	380±10	gsm	DIN53352 BS3424
Breaking Strength	650/502	N/5cm	DIN53354 BS3424
Tearing Strength	115/105	N	DIN53356 BS3424
Adhesion	60	N/5cm	DIN53357 BS3424
Width	Up to 510cm (0303 18*12 M)		
FR Certification	We can reach: M2, B1, DIN75200, NFPA701		
Lacquering	Products can be laquered with acrylic		
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3		
Ink Type	Solvent, Eco Solvent, UV, Screen Printing		



**Part Number: Laminated P 009-G**

Item	Metric		Test Method
Weight	440±10	gsm	DIN53352 BS3424
Breaking Strength	635/451	N/5cm	DIN53354 BS3424
Tearing Strength	125/107	N	DIN53356 BS3424
Adhesion	60	N/5cm	DIN53357 BS3424
Width	Up to 510cm (0305 18*12 G)		
FR Certification	We can reach: M2, B1, DIN75200, NFPA701		
Lacquering	Products can be laquered with acrylic		
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3		
Ink Type	Solvent, Eco Solvent, UV, Screen Printing		



**Part Number: Laminated P 009-M**

Item	Metric		Test Method
Weight	440±10	gsm	DIN53352 BS3424
Breaking Strength	635/451	N/5cm	DIN53354 BS3424
Tearing Strength	125/107	N	DIN53356 BS3424
Adhesion	60	N/5cm	DIN53357 BS3424
Width	Up to 510cm (0305 18*12 M)		
FR Certification	We can reach: M2, B1, DIN75200, NFPA701		
Lacquering	Products can be laquered with acrylic		
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3		
Ink Type	Solvent, Eco Solvent, UV, Screen Printing		



**Part Number: Laminated P 010-G**

Item	Metric		Test Method
Weight	440±10	gsm	DIN53352 BS3424
Breaking Strength	850/750	N/5cm	DIN53354 BS3424
Tearing Strength	185/135	N	DIN53356 BS3424
Adhesion	60	N/5cm	DIN53357 BS3424
Width	Up to 510cm (0505 9*9 G)		

<b>FR Certification</b>	We can reach: M2, B1, DIN75200, NFPA701
<b>Lacquering</b>	Products can be laquered with acrylic
<b>Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%</b>	We can reach: EN71-3
<b>Ink Type</b>	Solvent, Eco Solvent, UV, Screen Printing

**Part Number: Laminated P 010-M**

Item	Metric	Test Method
<b>Weight</b>	440±10 gsm	DIN53352 BS3424
<b>Breaking Strength</b>	850/750 N/5cm	DIN53354 BS3424
<b>Tearing Strength</b>	185/135 N	DIN53356 BS3424
<b>Adhesion</b>	60 N/5cm	DIN53357 BS3424
<b>Width</b>	Up to 510cm (0505 9*9 M)	
<b>FR Certification</b>	We can reach: M2, B1, DIN75200, NFPA701	
<b>Lacquering</b>	Products can be laquered with acrylic	
<b>Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%</b>	We can reach: EN71-3	
<b>Ink Type</b>	Solvent, Eco Solvent, UV, Screen Printing	

**Part Number: Laminated P 011-G**

Item	Metric	Test Method
<b>Weight</b>	440±10 gsm	DIN53352 BS3424
<b>Breaking Strength</b>	1350/1200 N/5cm	DIN53354 BS3424
<b>Tearing Strength</b>	245/185 N	DIN53356 BS3424
<b>Adhesion</b>	60 N/5cm	DIN53357 BS3424
<b>Width</b>	Up to 510cm (1010 9*9 G)	
<b>FR Certification</b>	We can reach: M2, B1, DIN75200, NFPA701	
<b>Lacquering</b>	Products can be laquered with acrylic	
<b>Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%</b>	We can reach: EN71-3	
<b>Ink Type</b>	Solvent, Eco Solvent, UV, Screen Printing	

**Part Number: Laminated P 011-M**

Item	Metric	Test Method
<b>Weight</b>	440±10 gsm	DIN53352 BS3424
<b>Breaking Strength</b>	1350/1200 N/5cm	DIN53354 BS3424
<b>Tearing Strength</b>	245/185 N	DIN53356 BS3424
<b>Adhesion</b>	60 N/5cm	DIN53357 BS3424
<b>Width</b>	Up to 510cm (1010 9*9 M)	
<b>FR Certification</b>	We can reach: M2, B1, DIN75200, NFPA701	
<b>Lacquering</b>	Products can be laquered with acrylic	
<b>Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%</b>	We can reach: EN71-3	
<b>Ink Type</b>	Solvent, Eco Solvent, UV, Screen Printing	

**Part Number: Laminated P 011-1-G**

Item	Metric	Test Method
<b>Weight</b>	510±10 gsm	DIN53352 BS3424
<b>Breaking Strength</b>	1350/1200 N/5cm	DIN53354 BS3424
<b>Tearing Strength</b>	245/185 N	DIN53356 BS3424
<b>Adhesion</b>	60 N/5cm	DIN53357 BS3424

Width	Up to 510cm (1010 9*9 G)
FR Certification	We can reach: M2, B1, DIN75200, NFPA701
Lacquering	Products can be laquered with acrylic
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3
Ink Type	Solvent, Eco Solvent, UV, Screen Printing

**Part Number: Laminated P 012**

Item	Metric	Test Method
Weight	610±10 gsm	DIN53352 BS3424
Breaking Strength	2100/1350 N/5cm	DIN53354 BS3424
Tearing Strength	200/300 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (1010 12*12 M)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

**Part Number: Coated P 013**

Item	Metric	Test Method
Weight	440±10 gsm	DIN53352 BS3424
Breaking Strength	1800/1300 N/5cm	DIN53354 BS3424
Tearing Strength	180/165 N	DIN53356 BS3424
Adhesion	80 N/5cm	DIN53357 BS3424
Width	Up to 510cm	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

**Part Number: Coated P 014**

Item	Metric	Test Method
Weight	510±10 gsm	DIN53352 BS3424
Breaking Strength	2200/1900 N/5cm	DIN53354 BS3424
Tearing Strength	300/250 N	DIN53356 BS3424
Adhesion	80 N/5cm	DIN53357 BS3424
Width	Up to 510cm	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

**Part Number: Coated P 015**

Item	Metric	Test Method
Weight	560±10 gsm	DIN53352 BS3424
Breaking Strength	2200/1900 N/5cm	DIN53354 BS3424
Tearing Strength	300/250 N	DIN53356 BS3424

<b>Adhesion</b>	80	N/5cm	DIN53357 BS3424
<b>Width</b>	Up to 510cm		
<b>FR Certification</b>	We can reach: M2, B1, DIN75200, NFPA701		
<b>Lacquering</b>	Products can be laquered with acrylic		
<b>Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%</b>	We can reach: EN71-3		
<b>Ink Type</b>	Solvent, Eco Solvent, UV, Screen Printing		

