

PVC MESH

Part Number: Coated P 006-1-G

Item	Metric	Test Method
Weight	270 gsm	DIN53352 BS3424
Breaking Strength	850/750 N/5cm	DIN53354 BS3424
Tearing Strength	185/155 N	DIN53356 BS3424
Adhesion	N/5cm	DIN53357 BS3424
Width	Up to 510cm (1010)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	

Part Number: Coated P 030

Item	Metric	Test Method
Weight	270 gsm	DIN53352 BS3424
Breaking Strength	850/1100 N/5cm	DIN53354 BS3424
Tearing Strength	200/215 N	DIN53356 BS3424
Adhesion	N/5cm	DIN53357 BS3424
Width	Up to 510cm (1010)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	

Part Number: Coated P 030-1

Item	Metric	Test Method
Weight	270 gsm	DIN53352 BS3424
Breaking Strength	1250/1100 N/5cm	DIN53354 BS3424
Tearing Strength	235/220 N	DIN53356 BS3424
Adhesion	60 N/5cm	DIN53357 BS3424
Width	Up to 510cm (1010 12*12)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	
Ink Type	Solvent, Eco Solvent, UV, Screen Printing	

Part Number: Coated P 031

Item	Metric	Test Method
Weight	270 gsm	DIN53352 BS3424
Breaking Strength	850/1100 N/5cm	DIN53354 BS3424
Tearing Strength	190/200 N	DIN53356 BS3424
Adhesion	N/5cm	DIN53357 BS3424
Width	Up to 510cm (0510)	
FR Certification	We can reach: M2, B1, DIN75200, NFPA701	
Lacquering	Products can be laquered with acrylic	
Cd%, Pb%, As%, Ba%, Cr%, Hg%, Se%	We can reach: EN71-3	